

# Screen Specification CC-1190 (-16 Mesh)



## U.S. Screen Size

Number	Opening	% Passing	Micron Range
8	2.360 mm	100	2360
16	1.180 mm	98.5 - 100	1180
30	0.600 mm	45 - 80	600
50	0.300 mm	15 - 40	300
100	0.150 mm	0 - 20	150
200	0.075 mm	0 - 10	75

## Iron Aggregate Analysis

Iron/Iron Oxide	Balance
Total Carbon	2.48
Manganese	0.93
Sulphur	0.12
Phosphorous	ND
Silicon	0.35
Nickel	>0.01
Chromium	>0.01
Vanadium	ND
Molybdenum	0.33
Copper	0.10
Aluminum	>0.01
Magnesium	0.01
Boron	0.01
Zinc	0.01
Zirconium	0.01

**CONNELLY – GPM, INC.**

ESTABLISHED 1875

3154 South California Avenue, Chicago, Illinois, 60608-5176

(773) 247-7231 | info@connellygpm.com | [www.ConnellyGPM.com](http://www.ConnellyGPM.com)

